







Product	Etching	Corrosion Protection	Filling	Color Holdout	Flexibility	Easy Sanding	Sand/Dry Time
----------------	----------------	-----------------------------	----------------	----------------------	--------------------	---------------------	----------------------

Super Etch	Excellent	Excellent	N/A	Must be sealed	Excellent	Not Recommended	30 Minutes
Etch Fill	Excellent	Excellent	Good	Good	Good	Excellent	30 Minutes
Fast Prime	Good	Excellent	Excellent	Excellent	Fair	Excellent	Excellent
Epoxy	N/A	Excellent	Good	Good	Excellent	Not Recommended	1-3 hours
Urethane	N/A	Good	Excellent	Excellent	Excellent	Excellent	1-2 hours
Hi-Prime	N/A	Fair	Good	Fair	Good	Excellent	20-30 minutes
Barrier Coat	N/A	Good	Excellent	Excellent	Good	Excellent	1 hour
Acrylic Sealer	NA	NA	Very Minor	Good	Excellent	Poor	20-30 min
Shade System 2K Sealer	NA	NA	Good	Excellent	Excellent	Fair	15-30 min



<u>PRODUCT</u>	<u>Mix Ratio</u>	<u>Application</u>	<u>Flash</u>	<u>Pot</u>	<u>Dust Free</u>	<u>Tack Free</u>	<u>Sand</u>	<u>Min-Max Recoat</u>	<u>Topcoat</u>
Super Etch	1:1 5' stirred	1 med coat	NA	24 hours	NA	NA	NA	30 min - 4 hours	Primer or sealer
Etch Fill	1:1	1-2 full wet	5-10 min	24 hours	NA	NA	NA	30 min - 24 hours	1-2 hours
VOC Epoxy Primer	4:1:1/2 5' stirred	1 full wet	NA	8 hours	NA	NA	1 hour	1 hour - 72 hours	1 hour
Fast Prime	4:1	2-3 full wet coats	5-10 min	2 hours	NA	NA	45 min	45-no max	45 min
Urethane Primer	4:1	2-3 med coats	10-15 min	3-4 hours	NA	NA	1-4 hours	3 - 12 hours	3-4 hours
Barrier Coat	RTS	2-3 full wet	15 min	Indefinite	NA	NA	30-60 min	60 min - no max	60 min
Hi Prime	2:3	2-3 full wet	10-15 min	Indefinite	NA	NA	20-30 min	30 min- no max	30 min
Acrylic Sealer	RTS	1-2 med coats	20 min	Indefinite	NA	NA	30 min	20 min - 48 hours	20 min
ShadeSys 2K Sealer	4:1	1 full wet coat	NA	2 hours	NA	NA	30 min	15-30 min	15-30 min
Production Clear	4:1	2-3 full wet coats	10 min	4-8 hours	5-10 min	15-25 min	16 hours	16 hours	NA
Quick Spot Clear	4:1	1 med +1 wet	5-10 min	0.5 - 1 hour	10 - 15 min	15- 17 min	2-7 hours	12 hours	NA
Urethane Clear V	4:1	1 med + 1 wet	10 -15 min	1.5-6 hours	10-30 min	25-60 min	Overnight	Overnight	NA
Hi Solids Clear	2:1	1 med + 1 wet	10-15 min	3-5 hours	15-20 min	30-45 min	Overnight	Overnight	NA

When it comes to quality abrasives, grinding & sanding, Autobody Master is the brand you can depend on.