



Neoprene

## Exceptional Grip in Wet and Dry Environments

- Excellent splash protection against a broad array of chemicals
- Tested for use with chemotherapy/cytotoxic drugs
- Neoprene formulation and textured fingertips provides a secure grip
- Polymer coated for easy donning



### Industries

- Life Sciences
- Chemical
- Healthcare

### Recommended For

- Loading centrifuges and chromatography columns
- Assembly of parts
- Sample taking and processing
- Blending, compounding solids and liquids
- Administering drugs
- Testing
- Maintenance
- Tested for use with chemotherapy drugs
- Enhanced grip in wet environments
- Damp donning
- Higher-risk clinical applications
- Protection from Type I latex allergy in HCW's or patients



## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

	<b>NeoPro</b> <sup>®</sup> <b>NPG-888</b>
<b>Material</b>	Neoprene (Polychloroprene)
<b>Color</b>	Green
<b>Glove Design</b>	Polymer Coated, Powder-Free, Textured Fingers
<b>Cuff</b>	Beaded
<b>Manufacturing/QMS Audit Standards</b>	EN ISO 13485 : 2012
<b>Regulatory/Standards Compliance</b>	ASTM D6977, EN 420:2003 + A1:2009, FDA21 CFR 177-2600, US QSR/FDA 510(k) Medical Examination Grade
<b>Packaging</b>	100 gloves per dispenser 10 dispensers per case 1000 gloves per case
<b>Storage</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition
<b>Country of Origin</b>	Indonesia
<b>User Needs Segment</b>	Robust

### PHYSICAL PROPERTIES

	Typical Values		Testing Method
	BEFORE AGING	AFTER AGING	
Length (mm/inches)	245 / 9.6		ASTM D3767,EN420
Freedom from Holes (Inspection level I)	1.5 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/inches)	0.13 / 5.1		ASTM D3767,EN420
Finger Thickness (mm/inches)	0.17 / 6.7		ASTM D3767,EN420
Ultimate Tensile Strength (MPa)	≥ 24	≥ 18	ASTM D412 & D573
Elongation at Break (%)	≥ 650	≥ 400	ASTM D412
Force at break (N)	≥ 9	≥ 9	ASTM D6977