


Designed to enhance safety by offering extra durability

- Three times thicker than standard latex gloves to prevent rips, snags and tears
- Soft, elastic fit and feel
- Textured fingertips provide secure grip
- Extended cuff for expanded protection over the wrist and forearm
- Double chlorinated for easy donning and a comfortable feel
- Certified to the emergency medical glove requirements of NFPA 1999



Industries

- Automotive
- Automotive Aftermarket
- Life Sciences
- Healthcare

Recommended For

- Inspection, selecting, checking parts
- Assembly and inspection of components
- Picking and fastening components
- Equipment repair and maintenance
- General Purpose Auto Aftermarket
- Body panel repair and replacement
- Tire rotation & changes
- Animal care feeding and cleanup
- Maintaining lab furniture and equipment
- Sample taking and processing
- Raw material sample collection
- Extra protection over the wrist and arm
- Higher-risk clinical applications
- Tested for use with chemotherapy drugs



TECHNICAL DATA SHEET

PRODUCT INFORMATION

	SafeGrip[®] SG-375
Material	Natural Rubber Latex
Color	Blue
Glove Design	Chlorinated, Powder-Free, Textured Fingers
Cuff	Beaded
Manufacturing/QMS Audit Standards	EN ISO 13485 : 2012
Regulatory/Standards Compliance	ASTM D3578, EN 420:2003 + A1:2009, FDA21 CFR 177-2600, NFPA 1999:2013, US QSR/FDA 510(k) Medical Examination Grade
Packaging	50 gloves per dispenser 10 dispensers per case 500 gloves per case
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition
Country of Origin	Malaysia
User Needs Segment	High Risk
Available sizes	S (6.5 - 7), M (7.5 - 8), L (8.5 - 9), XL (9.5 - 10)

PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	295 / 11.6		ASTM D3767,EN420
Freedom from Holes (Inspection level I)	1.5 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/inches)	0.28 / 11		ASTM D3767,EN420
Finger Thickness (mm/inches)	0.36 / 14.2		ASTM D3767,EN420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	≥ 34	≥ 21	ASTM D412 & D573
Elongation at Break (%)	≥ 850	≥ 750	ASTM D412
Force at break (N)	≥ 15	≥ 10	EN 455-2