TEGHNIGAL DATA SHEET - FUZIONIM

PRODUCT: FUZION™ Lightweight Filler



DESCRIPTION:

FUZION™ Lightweight Filler is formulated with patent pending N-TEK for maximum adhesion to galvanized, steel, aluminum and all metals. Formulated to deliver an easy-to-spread and easy-to-sand finish, FUZION is clog free, tack free and ideal for use on all metal surfaces.

PART NUMBERS:

•	16000 FUZION™ Gallon	4 gallons / case	31 lbs / case
•	16001 FUZION™ 3 Gallon Mechanical	1 / case	23 lbs / case
•	16002 FUZION™ 3 Gallon Air Pail	2 / case	44 lbs / case
•	16003 FUZION™ 5 Gallon Air Pail	1 / case	37 lbs / case

PRODUCT USES:

Use for filling and repair of bodywork up to ¼", such as dents, dings, scratches, hail damage and small holes.

TYPICAL SUBSTRATES:

- Steel
 Aluminum
 Fiberglass
 Body Filler
 Wood
 2K Primers
- Aged, sanded OEM Topcoats
 Galvanized and other zinc-coated steel
- SMC can be used for cosmetic repairs. For structural repairs prone to high degrees of stress and flexibility, use an SMC repair product.



SURFACE PREPARATION:

- 1. Clean surface. Remove all dirt, oil, grease and wax with a cleaning solvent such as #1240-1 Wax, Grease & Silicone Remover.
- 2. Make sure surface is dry before repairing.
- 3. Use 40-80 grit disc to featheredge paint for good mechanical adhesion.



MIXING:

For best results, bring filler and provided hardener to room temperature (minimum temperature 75°F). Stir product before dispensing with a bottom to top motion. Knead hardener tube before use. Place a 4" diameter puddle of filler on a clean mixing surface (we recommend a non-absorbent plastic mixing board) and add a ribbon of cream hardener from edge to edge across the center of the filler puddle (puddles larger than 4" will require additional hardener); or measure hardener at 2% by weight of filler – a 50 to 1 ratio. Mix thoroughly with a plastic spreader, using a folding motion, until uniform color is achieved. At room temperature (75°F) approximate setting time is 3 – 5 minutes.

APPLICATION:

- 1. Using a plastic spreader, apply a thin layer of filler to surface, using firm pressure for maximum adhesion.
- 2. Apply additional layers, if necessary, building up damaged area higher than surrounding metal surface to allow for sanding of filler.
- 3. IMPORTANT! DO NOT RETURN UNUSED MIXTURE TO CAN AS IT WILL HARDEN THE REMAINING CONTENTS.

FINISHING:

- 1. When material has cured, in approximately 15 minutes, sand with a 80-120 grit sandpaper.
- 2. Finish sand with 180-240 grit.

TOPCOATING:

May be topcoated with polyester, 2K urethane or 1K primer. Refer to paint manufacturer's instructions for topcoat application.

SPECIAL NOTES:

May be intermixed with PRO-GLAZE™, BLAZE GLAZE™, or Icing® or thinned with SUPER CHARGER™.



TECHNICAL INFORMATION:

Appearance as Packaged:

VOC

Weight Per Gallon (Density):

Maximum Recommended Thickness (sanded):

Viscosity @ 77°F Gel Time @ 77°F:

Shore "D" Hardness Values @ 24 hours:

Sanding Time @ 77° F: Catalyst Required: Catalyzation Ratio: Exotherm Temperature: Tack Free Time:

Maximum Heat:

Light Blue

Packaged: 215 g/l Applied: 0.8 g/l

8.45 pounds (Average)

1/4"

94,000 cps (Average) 3.0 - 5.0 minutes

50 - 55

15-20 minutes
Benzoyl Peroxide
2% by weight
220°F (Average)
10 – 15 minutes
200°F for 30 minutes

ASSOCIATED MSDS: Filler: "Fuzion-15041" Hardener: "Cream Hardener"



HEALTH & SAFETY:

Read all warnings, first aid and safety for all components before using. Keep out of reach of children and animals. Protect hands with impervious rubber gloves. Wear face, skin and eye protection. When sanding, we recommend the use of a respiratory covering device to protect from dust (MSA mask P/N 459029 with MSA cartridge 464029 or equivalent). When using power equipment, refer to power tool manufacturer's recommendations for safety equipment. USC products are for industrial use by trained professionals only.